



EL-BOUR
شركة العبور لإنتاج الورق ش.م.م
El-Obour for Paper Production

| | |
|-----------------|----------------|
| Product: | Fluting 90 GSM |
|-----------------|----------------|

| Test Type | Units | Average | Tolerance |
|---------------|----------|---------|-----------|
| Grade | GSM | 90 | ±5% |
| Thickness | mm | 0.18 | ±5% |
| Bursting | kPa | 180 | ±5% |
| Moisture | % | 7 | ±1% |
| CMT | N | 150 | ±5% |
| R.C.T (C.D) | kN/m | 0.7 | ±5% |
| R.C.T (M.D) | kN/m | 0.5 | ±5% |
| Tensile (C.D) | kgf/15mm | 2.5 | ±5% |
| Tensile (M.D) | kgf/15mm | 5.3 | ±5% |

| | |
|-----------------------|--|
| Core: | 10 cm is the standard size. |
| Reel Width: | Minimum width is 50 cm. Maximum width is 200 cm. The trimmed width of the paper machines is 3.5 m. |
| Marking: | Printed on the core. The label is on the belly. |
| Reel Diameter: | 120-140 cm. |
| Reel Wrapping: | Paper end is both glued and taped. |